

## RTV Silicone Adhesive KN-300X

### Products Description

RTV adhesive KN-300X one component, ready-to-use adhesive sealants are extremely versatile. It cures to be silicone rubber at room temperature by exposure to ambient moisture to form a tough, elastic bond between cured type of silicone rubbers as preferably

RTV adhesive KN-300X are standard strength paste consistency which can be applied to stick silicone glue to nylon, glass, clothes, plastic and so on. It's characterized by temperature resistance (-60~200°C), ozone resistance, UV-Resistance and electrical insulating property.

### Physical properties

**Appearance:** Colorless and semi-transparent gel

**Viscosity:** 60kg/cm<sup>2</sup>

**Elongation:** 300%

### Usage One: Silicone rubber to silicone rubber at room temperature.

- 1, Cleaning: Cleaning the bonding surface.
- 2, Gluing: The gluing thickness equal and less than 5mm
- 3, Pressing: More than 120 minutes pressing, Absolutely cured after 24 hours at 25°C.

### Usage TWO: Silicone rubber to plastic at room temperature

- 1, Cleaning: Cleaning the bonding surface with toluene or absolute ethyl alcohol.
- 2, Activating: Brushing fewer adhesive (CL-24J) on the cleaned surface. (single brushing is enough)
- 3, Curing: Curing at room temperature for 30 minutes
- 4, Gluing: After adhesive cured, Brushing KN-300 on the bonding surface, pressing over 120 minutes, Absolutely cured after 24 hours at 25°C

### Attention

- KN-300X is easy to cure once contacting with moisture, it must be stored in a completely sealed and dark place.
- Avoid eye contact. If irritation occurs, flush eye(s) with lukewarm gently flowing water for 5

Add: H Building, XinWei 3rd industrial area, DaLang Street, LongHua Town, Baoan District, Shenzhen City, Guangdong Province, China

Tel: +86-755-81478876-8018

Fax: +86-755-81478372

Mobile phone: 0086 138 2374 7978

Email: [export@klbsilicone.com](mailto:export@klbsilicone.com)

Website: [www.all-glue.com](http://www.all-glue.com)

minutes. Obtain medical attention.

- Please fasten down the the cover after using to avoid the gel to be cured.

## Packing

100g/Piece or 330g/ Piece



Add:H Building,XinWei 3rd industrial area,DaLang Street, LongHua Town,Baoan District , Shenzhen City, Guangdong Province,China

Tel: +86-755-81478876-8018

Fax: +86-755-81478372

Mobile phone :0086 138 2374 7978

Email: [export@klbsilicone.com](mailto:export@klbsilicone.com)

Website: [www.all-glue.com](http://www.all-glue.com)